


BluLight™ Primary Tube

(Thin Walled Tube)
10/8mm_White



1. General Description

BluLight™ Primary Tube is coated with silicone and suitable for fiber blowing with low friction.

2. Primary Tubes Technical Details

2-1 Dimension


Outer diameter(mm)		Inner diameter(mm)		Wall thickness(mm)		Pressure(bar)		Rib Depth(mm)	
Nominal	Tolerance	Nominal	Tolerance	Nominal	Tolerance	Max	Operation	Nominal	Tolerance
10	±0.1	8	±0.1	1.0	±0.1	16	10	0.1	±0.05

2-2 Marking

The microduct marking shall include the following information: (Frequency - repeated every 1meter)

- Project Name (e.g. ALLIANDER)
- Tube type(e.g. R)
- Product spec.(e.g 10/8mm)
- Manufacturer (e.g. LGCE-KNET)
- Spec No.(e.g. LGCE-23-DM2044-00)
- Manufactured code(e.g YYMMDD 2A01)
- Length marking(e.g. = 0001m =)

※ Example



3. Configuration & Color

- Microduct(primary tube) : Polyethylene tube, White
Silicone coating and smooth or straight ribbed inner surface
- Other colors are available upon the customer request.

4. Mechanical Performance test

Mechanical properties	International standard	Test conditions	Performance
Inner clearance	IEC 60794-5-10 Annex E	Pressure : 12bar Max. Sphere size : 85% of nom. ID	Pass : Pass through the primary tube.
Tensile Strength	IEC 60794-5-10&20	Tube length under tension: >1m Max. Tensile load: 1.1 x 9.8 x W*[N] Duration of max. load: 10 min *W = mass of 1km of component in kg	Pass: Under visual examination without magnification, There shall be no damage and then the inner clearance test shall be passed..

Crush	IEC 60794-5-10&20	Sample length : Load: Duration of Max. load: Recovery time:	250mm 700N 1 minute 1 hr	Pass: The outer and inner diameter of the duct shall show, under visual examination without magnification no damage and then the inner clearance test shall be passed.
Impact	IEC 60794-5-10&20	Striking surface radius: Impact: Number of impact: Recovery time:	300mm 1 J 3 1 hr	Pass: Under visual examination without magnification, there shall be no damage to the duct, no splitting or permanent damage and then the inner clearance test shall be passed. The imprint of the anvil on the sheath is not considered as mechanical damage.
Kink	IEC 60794-5-10&20	Diameter:	$\leq 20 \times OD$	Pass: The outer and inner diameter of the duct shall show, under visual examination without magnification no damage and then the inner clearance test shall be passed.
Bend	IEC 60794-5-10&20	Number of turns: Mandrel diameter: Number of cycles:	5 $\leq 24 \times OD$ 3	Pass: The outer and inner diameter of the duct shall show, under visual examination without magnification no damage and then the inner clearance test shall be passed.

5. Packing

Primary tubes are delivered on drum.

Product Code	Length/drum(m)	Drum size(H x W)	Gross weight(kg)	Number of Drums in 40'(EA)
PT10/8	2,000	1,070 x 380	76	110

6. Internationally Certified

Microduct Assemblies has been rigorously tested by Telcordia Technologies and found to be compliant with Telcordia GR-3155-CORE.



This specification is intended as a guide only. Whilst the information it contains is believed to be correct, LGCE can take no responsibility for action taken based on the information contained in this document. LGCE reserved the right to make changes to this document without notice. All sales of product are subject to LGCE's terms and conditions of sales only. Any unauthorized copying of this document or our products is prohibited and LGCE will take action to prevent any infringement of its rights and to claim damages for the loss that it suffers.